



TEXCRETE[®]

WB TEXTURE WATERPROOFER

SMOOTH TEXTURE 3194 LINE

Features

- Waterborne Masonry Waterproofer
- High Build
- Low VOC
- Tilt-Up
- Pre-Cast
- CMU
- Stucco
- Other Vertical Masonry Surfaces

Recommended For

- For commercial and residential applications
- Use on exterior vertical masonry substrates in exposures ranging from mild atmospheric to extreme weathering and wind-driven rain. These products may be applied to cured or uncured (green) concrete (minimum cure 10 days). No need to wait the required 28 day for concrete to cure.

General Description

Coronado[®] Texcrete[®] WB Waterproofer is high build, low VOC, breathable waterproofing coatings, designed for application by the professional contractor to above grade concrete and masonry structures. These coatings are specifically engineered to be applied direct to concrete and masonry surfaces without priming. Texcrete[®] WB coatings are designed to resist high pH surfaces and therefore can be applied direct to new concrete without extended curing and delays. These coatings are resistant to salt spray, wind driven rain (up to 100 mph), acid rain and UV light. The breathable, high build film allows moisture vapor to pass through, without blistering or causing a loss of adhesion. Available in various textures, these products do not require a primer / filler on smooth masonry surfaces.

Limitations

- May be applied to cured or uncured (green) concrete in temperatures ranging from 35°F up to 95°F.

Product Information

<p>Colors — Standard: White</p> <p>— Tint Bases: N/A Can be tinted with up to 2 oz per gallon of Universal (Glycol) Colorants to achieve pastel to midtone type colors.</p> <p>— Special Colors: Contact your dealer.</p> <p>Certification: The products supported by this data sheet contain a maximum of 100 grams per liter VOC / VOS (0.83 lbs/gal.) excluding water & exempt solvents. This product is compliant under the Ozone Transport Commission regulations as a Waterproofing Concrete/Masonry Sealer. This product line does meet the qualifications for LEED (Leadership in Energy and Environmental Design) projects if used as a Waterproofing Coating.</p> <p>Technical Assistance: Available through your local authorized independent dealer. For the location of the dealer nearest you, call 1-800-225-5554, see www.coronadopaint.com or consult your local Yellow Pages.</p>	<p>Technical Data ◊ White</p> <table border="1"> <tr> <td>Vehicle Type</td> <td>Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>37.8 ± 1.0%</td> </tr> <tr> <td>Coverage per Gallon at Recommended Film Thickness</td> <td>90 – 110 Sq. Ft.</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 16.0 mils – Dry 6.1 mils</td> </tr> <tr> <td colspan="2">Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.</td> </tr> <tr> <td>Dry Time @ 77°F (25°C) @ 50% RH</td> <td>– Tack Free 1 Hour – To Recoat 4 Hours</td> </tr> <tr> <td colspan="2">High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td>Evaporation</td> </tr> <tr> <td>Viscosity</td> <td>115 – 120 KU</td> </tr> <tr> <td>Flash Point</td> <td>200°F or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Flat</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min. 35°F – Max. 95°F</td> </tr> <tr> <td>Thin With</td> <td>Not Recommended</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Warm Soapy Water</td> </tr> <tr> <td>Weight Per Gallon</td> <td>11.5 lbs</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min. 45°F – Max. 95°F</td> </tr> <tr> <td colspan="2">Volatile Organic Compounds (VOC) 91 Grams/Liter 0.80 Lbs./Gallon</td> </tr> </table>	Vehicle Type	Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	37.8 ± 1.0%	Coverage per Gallon at Recommended Film Thickness	90 – 110 Sq. Ft.	Recommended Film Thickness	– Wet 16.0 mils – Dry 6.1 mils	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.		Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free 1 Hour – To Recoat 4 Hours	High humidity and cool temperatures will result in longer dry, recoat and service times.		Dries By	Evaporation	Viscosity	115 – 120 KU	Flash Point	200°F or greater (TT-P-141, Method 4293)	Gloss / Sheen	Flat	Surface Temperature at Application	– Min. 35°F – Max. 95°F	Thin With	Not Recommended	Clean Up Thinner	Warm Soapy Water	Weight Per Gallon	11.5 lbs	Storage Temperature	– Min. 45°F – Max. 95°F	Volatile Organic Compounds (VOC) 91 Grams/Liter 0.80 Lbs./Gallon	
Vehicle Type	Acrylic																																				
Pigment Type	Titanium Dioxide																																				
Volume Solids	37.8 ± 1.0%																																				
Coverage per Gallon at Recommended Film Thickness	90 – 110 Sq. Ft.																																				
Recommended Film Thickness	– Wet 16.0 mils – Dry 6.1 mils																																				
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint.																																					
Dry Time @ 77°F (25°C) @ 50% RH	– Tack Free 1 Hour – To Recoat 4 Hours																																				
High humidity and cool temperatures will result in longer dry, recoat and service times.																																					
Dries By	Evaporation																																				
Viscosity	115 – 120 KU																																				
Flash Point	200°F or greater (TT-P-141, Method 4293)																																				
Gloss / Sheen	Flat																																				
Surface Temperature at Application	– Min. 35°F – Max. 95°F																																				
Thin With	Not Recommended																																				
Clean Up Thinner	Warm Soapy Water																																				
Weight Per Gallon	11.5 lbs																																				
Storage Temperature	– Min. 45°F – Max. 95°F																																				
Volatile Organic Compounds (VOC) 91 Grams/Liter 0.80 Lbs./Gallon																																					

◊ Reported values are for White. Contact your dealer for values of other bases or colors.

Texcrete® WB Texture Waterproofer Smooth Texture 3194 Line

Surface Preparation

New, Uncoated Surfaces: Must be free of dirt, dust, oil, grease, wax, form release, curing compounds or other debris that may affect penetration and adhesion. Remove efflorescence, laitance, chalk and other contaminants utilizing industry accepted standards. Surface projections, mortar spatter and other protrusions should be removed by grinding or scraping. Mortar joints should be raked. Large "bug holes" or gravel pocks should be filled with mortar, or cementitious patching materials and allowed to cure before continuing. Damp masonry surfaces may be coated, however, no visible signs of water should be present on the surface.

Previously Coated Surfaces: Must be dry and free of dirt, dust, chalk, and other contaminants which may interfere with adhesion. Remove these by pressure washing with adequate pressure and water movement to ensure complete removal of contaminants. Loose or failing previous coating should be removed back to the point of sound adhesion. Existing coatings should be checked for compatibility with Coronado® Texcrete® WB Waterproofer by the application of a test patches.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Cracks, voids, transitions, changes of angle and junctions or dissimilar materials should be cleaned, primed with Coronado® 48 Line Acrylic Masonry Sealer and then patched with Coronado® Elastomeric Patching Compounds or a high quality acrylic urethane sealant, and these materials should be allowed to completely dry. Failing mortar joints should be replaced and tuck-pointed with new mortar. Large "bug holes" or gravel pocks should be filled with mortar or cementitious patching materials and allowed to cure before continuing. Smooth masonry does not need a sealer, however if the substrate has some porosity, the smooth grade (3194 Line) or sand texture (3192 Line) should be used as the first coat.

Stir product thoroughly prior to use. Apply product by spray, or roller (for smaller areas) to be determined by job conditions, size and applicator preference.

Airless Spray: Best accomplished by using a pump capable of spraying textured materials, such as the Graco GM5000 or Graco TexSpray 1030, and a .X39 tip.

NOTE: Medium and Coarse Textures may experience packing in commercially available airless tips. If this occurs, apply by hopper type gun or power roller. Sprayed finishes must be knocked off using a 3/4" to 1" lambs wool cover or loop roller to ensure uniform coverage. Knock Off is best accomplished in vertical passes down the wall, lifting the roller away from the wall at the end of each downward stroke.

Roller or Power Roller: Apply in 2 cross hatch coats (perpendicular to one another), utilizing a 1 inch lambs wool cover. Apply 9 to 10 mils wet per coat. Follow drying schedule listed in Technical Data Table above before applying second coat.

Typical system is either two coats of the same texture or on porous masonry (such as CMU or split faced) one coat of smooth or sand finish, followed by the desired texture finish coat. See technical data sheet for any additional information.

THINNING: Not recommended, however in hot weather, thin with water.

Cleanup

Clean all tools and equipment with warm, soapy water.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry empty containers may be recycled in a can recycling program. **Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.**

Environmental, Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING: This product contains a chemical known to the state of California to cause cancer and birth defects, or other reproductive harm.

FIRST AID: In case of eye contact, flush immediately with plenty of water for at least 15 minutes; for skin, wash thoroughly with soap and water. If symptoms persist, seek medical attention. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

IN CASE OF SPILL – Absorb with inert material and dispose of as specified under "Cleanup".

KEEP OUT OF REACH OF CHILDREN

PROTECT FROM FREEZING

Refer to Material Safety Data Sheet for additional health and safety information.